

# **LUCAS** *Coatings & Mastics for the Waterproofing Trade*

R. M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300 rmlucas.com

## **PRODUCT DATA BULLETIN**

### **#2900 CLEAR ACRYLIC MASONRY SEALANT**

#### **PURPOSE**

Lucas #2900 Clear Acrylic Masonry Sealant is an elastomeric protective coating intended for application to concrete and masonry walls. Lucas #2900 prevents moisture penetration of the masonry surfaces while allowing the passage of moisture vapor out of the wall to prevent spalling. The high elongation exhibited by this product allows it to bridge non-structural cracks. #2900 will alter the appearance of masonry and concrete, causing it to look slightly darker. Non-yellowing.

#### **PRODUCT DESCRIPTION**

Lucas #2900 is formulated from 100% acrylic polymers. This is a water-based material and must be kept from freezing.

#### **APPLICATION**

Mechanically mix before using. Do not store above 90°F. Apply only at temperatures above 40°F and rising with less than 90% humidity and no threat of rain for 48 hours. Horizontal surfaces must be power-washed clean with a suitable residue-free detergent such as Lucas #115. The surface may be damp but must be free of standing water. Surface temperatures should be under 100°F to avoid premature curing.

This product displays very good resistance to intermittent ponding water. However, when applied to areas that retain water permanently or near-permanently, service life will be severely diminished and adhesion failure can be expected.

Caulk any existing cracks or penetrations with Lucas #2500 prior to application of the coating and allow to dry. Apply with a roller or suitable spray equipment at the rate of one gallon per 100 sq. ft. Irregular surfaces such as split-face block will require more material. A second coat is required on horizontal surfaces. Spray application is preferred as it will yield a smoother surface that will be less likely to pick up dirt. Drying time to second coat @ 70°F is 2 to 4 hours. Clean up uncured coating with soap and water.

## CAUTION

Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. Keep out of reach of children. Read MSDS prior to use.

### #2900 SPECIFICATION

Viscosity ASTM D-562	2000 cps @ 77°F (25°C)
Recommended rate of application	1 gal. per 100 sq. ft
% Elongation	400 min
% Solids	40 min
Weight per gallon	9.2 lbs.
Flash Point (TCC)	None
Container Sizes	5, 55, 250 gal tote
Colors	NA

Information contained in this bulletin is offered gratis on the basis of our field experience and laboratory tests conducted carefully using modern equipment verified for accuracy. No warranty is expressed or implied beyond the purchase price of the material. We suggest that the user evaluate the product's suitability for a particular use prior to application. We reserve the right to improve, change, or discontinue specifications and products without prior notice.