

LUCAS *Coatings & Mastics for the Roofing Trade*

R. M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300 rmlucas.com

PRODUCT DATA BULLETIN

#714 FIBRATED LIQUID ROOF COATING - PREMIUM

PURPOSE

Lucas #714 Fibrated Liquid Roof Coating provides an economical means of recoating and preserving smooth-surface asphalt roofs. Periodic recoating of otherwise sound built-up roofing felts can prolong service life many years. Deteriorated roofs can often be restored with the use of polyester fabric and select asphalt coatings. Please refer to our Polyester Roofing Systems literature.

This product is not intended for use over tar or asphalt and gravel roofs. Please refer to our #010 for tar roofs and #713 for asphalt and gravel roofs.

PRODUCT DESCRIPTION

Lucas #714 is formulated from refined higher softening point asphalt, non-asbestos reinforcing fibers and petroleum solvents. Consistency is maintained to provide easy brushing qualities with sufficient stability to avoid running or sagging when applied as directed. #714 is formulated to dry more quickly than standard grade products and is less susceptible to oxidative degradation. All of our asphalt roof coatings are ready to use and do not require special preparation before use.

APPLICATION

Surface to be coated must be clean and dry. Weak, broken, cracked or blistered areas of the roof and flashings must be repaired prior to coating with #714. Blisters, which are caused by trapped moisture, must be opened and dried, then resealed using glass membrane and Lucas #771 Plastic Roof Cement. Moisture trapped between plies of a roof will eventually reappear as a blister or a leak. Apply #714 evenly, as it comes from the container with any appropriate tool, preferably, a four knot roofing brush, at the rate of approximately three gallons per 100 square feet. Do not allow foot traffic until the coating is fully cured. Clean up with mineral spirits or waterless hand cleaner.

CAUTION

Combustible mixture, keep away from heat and open flames. Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. Do not use near heat or open flame. Keep out of reach of children. Read MSDS prior to use.

#714 SPECIFICATION

Applicable Specification Fed. Spec. Viscosity ASTM D-562 (Mid-Season Grade)	ASTM D 4479 Type I SS-A-694D 900 g @ 77°F (25°C) 4500 cps
Recommended rate of application	3 gal. Per 100 sq. ft.
% Asphalt	42 min
% Solids	46 min
% Non-volatile	75 max
Weight per gallon	7.9 lbs.
Flash Point (TCC)	100°F + (38.7°C)
Container Sizes	1, 5, 55, Bulk

Information contained in this bulletin is offered gratis on the basis of our field experience and laboratory tests conducted carefully using modern equipment verified for accuracy. No warranty is expressed or implied beyond the purchase price of the material. We suggest that the user evaluate the product's suitability for a particular use prior to application. We reserve the right to improve, change, or discontinue specifications and products without prior notice.