



LUCAS Professional Coatings, Sealants & Adhesives

R.M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300 rmlucas.com

#6700 TERPOLYMER GUTTER SEAL

#6700 SPECIFICATION

ASTM C-920, Type S, Grade S & NS, Class 25, Use NT, M, G, A & O - except for weight loss.

PRODUCT DESCRIPTION

Lucas #6700 Terpolymer Gutter Seal is a high-performance, multipurpose thermoplastic elastomer based sealant intended for the installation and repair of aluminum gutters. Excellent adhesion to most surfaces including: metal, Kynar®, asphalt, shingles, modified bitumen, EPDM, TPO, Elvaloy/PVC, Hypalon, vinyl, fiber cement, wood, concrete, tile, masonry, glass. #6700 is available in non-sag and self-leveling formulations.

APPLICATION

Surface to be sealed must be clean. To use, cut tip to size and puncture seal. When joining new gutters, apply two 1/4 inch beads to the lap area 1.5 to 2 inches apart. Mate the gutter sections together and fasten each side with a screw or pop rivet. Apply a 1/2 inch bead to the top of the seam and to all factory seams. Tool to 1/4 inch thick to avoid damming water. May be painted. Some paints may require up to one week cure time before application. Keep product warm prior to use.

Clean up: Clean up with Lucas #125 Safe Solve™.

Shelf Life: Two years from the date of manufacture.

WARNING! COMBUSTIBLE LIQUID AND VAPOR. Contains petroleum distillates. Keep away from heat and open flames. Avoid prolonged contact with or inhalation of solvent fumes. A NIOSH approved respirator with organic vapor cartridges is recommended. Do not take internally. If swallowed, do not induce vomiting. Contact medical personnel immediately. Read SDS prior to use. For professional use only. Emergency phone number 1-800-424-9300.

California Proposition 65 Warning: This product may contain chemicals known to the State of California to cause cancer, birth defects and/or reproductive harm.

Viscosity	ASTM D 2196	1,300,000 cps
Solids by Weight	ASTM D 1644	70%
Solids by Volume	ASTM D 2697	67%
Weight Per Gallon	ASTM D 1147	8 lbs.
Tensile Strength	ASTM D 2370	700 psi
Elongation	ASTM D 2370	1000%
Movement	ASTM C 719	+/-25%
Skin Time	ASTM C 679	30 Minutes
Tack Free	ASTM C 679	3 Hours
Flash Point	ASTM D 56	103°F / 39°C
VOC (Clear)	EPA 24	< 30%
VOC (White)	EPA 24	< 1.5%

Above values are for Clear

Container Sizes: 10 oz. fiber cartridge

Colors: Clear, White

TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.