



LUCAS Professional Coatings, Sealants & Adhesives

R.M. Lucas Co. 3211 S. Wood St. Chicago, IL 60608 (773) 523-4300 rmlucas.com

#500 RUBBERIZED ASPHALT WATERPOOFING MEMBRANE

#500 SPECIFICATION

ASTM D 1227 Type III, Class 2
ASTM D 1187 Type II
ASTM C 836
IRC 406.1- 406.2
IBC 1801.2 -1801.3

PRODUCT DESCRIPTION

#500 Rubberized Asphalt Waterproofing Membrane is a water-based rubberized asphalt protective coating for concrete and block foundations. Low modulus and extremely high elongation allow bridging of non-structural foundation cracks and resistance to hydrostatic pressure.

Lucas #500 Rubberized Asphalt Waterproofing Membrane is manufactured from refined asphalts, polymer modifiers and anionic surfactants. #500 has a brown appearance when wet but will dry to a near black color.

APPLICATION

Lucas #500 Rubberized Asphalt Waterproofing Membrane may only be applied when temperatures are expected to remain above 20°F for the next 24 hours. Surface must be clean. Apply with suitable spray equipment, roller or brush at the rate of 3.75 to 4 gallons per 100 sq. ft. to obtain a 40 mil dry film thickness as required by the International Residential Code. Spray and cold weather applications require heating of the product to 110-140°F.

Protection board and drain tile is recommended to drain water away from the foundation wall. Please contact Lucas Technical Support for complete Lucas TPS500 Waterproofing System guide specifications including installation instructions.

Clean Up: Wet coating soap and water. Dry coating Lucas #125 Safe Solve™.

Shelf Life: 1 year minimum.

CAUTION: Avoid prolonged contact with or inhalation of fumes. Do not take internally. If swallowed, do not induce vomiting. Contact medical personnel immediately. Read SDS prior to use. For professional use only. Emergency phone number 1-800-424-9300.

California Proposition 65 Warning: This product may contain chemicals known to the State of California to cause cancer, birth defects and/or reproductive harm.

Viscosity	ASTM D 2196	40,000 cps
Solids by Weight	ASTM D 1644	64%
Solids by Volume	ASTM D 2697	65%
Weight Per Gallon	ASTM D 1147	8.2 lbs.
Elongation	ASTM D 412	>2000%
Adhesion	ASTM C 836	Pass
Vapor Permeance	ASTM E 96	< 1 perm
Crack Bridging	ASTM C 836	10 cycles Pass
Hydrostatic Head	ASTM D 5385	96" @ 40 mils
Mold Growth	ASTM D 3273	None
Bacterial Growth	ASTM D 3274	None
Flash Point	ASTM D 56	NA
VOC	EPA 24	<5 g/l

Container Sizes: 5, 55, 275 gallon

Colors: Black

TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.