



## #6600 UNIVERSAL TERPOLYMER SEALANT



### PRODUCT DESCRIPTION

Lucas #6600 Universal™ Sealant is a high-performance, multipurpose thermoplastic elastomer based roofing sealant. Excellent adhesion to most surfaces including: metal, Kynar®, asphalt, shingles, modified bitumen, EPDM, TPO, Elvaloy/PVC, Hypalon, vinyl, fiber cement, wood, concrete, tile, masonry, glass. #6600 is available in clear, black, white and various colors. It is also available in three grades: Standard caulking grade, Self-Leveling Grade (#6600SL) and Winter Grade (#6600W). Use to seal seams, flashings and penetrations on all types of roofs. Ideal for residential roofing applications where appearance is important.

### APPLICATION

Surface to be sealed must be clean. Porous surfaces may be primed with Lucas #5015 prior to application of this product. To use, cut tip to size and puncture seal. Maximum recommended joint width and depth is 3/8 inch. Use backer rod for deep joints. Please read the most current Lucas Product Data Bulletin and SDS for this product prior to use. #6600 may be painted. Some paints may require up to one week cure time before application. Keep product warm prior to use. A Winter Grade formula, #6600W, is available for extreme cold weather applications.

Clean up: Clean up with Lucas #125 Safe Solve™.

Shelf Life: Five years from the date of manufacture.

**WARNING! COMBUSTIBLE LIQUID AND VAPOR.** Contains petroleum distillates. Keep away from heat and open flames. Avoid prolonged contact with or inhalation of solvent fumes. A NIOSH approved respirator with organic vapor cartridges is recommended. Do not take internally. If swallowed, do not induce vomiting. Contact medical personnel immediately. Read SDS prior to use. For professional use only. Emergency phone number 1-800-424-9300.

### #6600 SPECIFICATION

ASTM C-920, Type S, Grade NS, Class 25, Use NT, I, M, G, A & O - except for weight loss.  
 Fed Spec TT-S-00230c, Class A, Type II

Viscosity	ASTM D 2196	1,800,000 cps
Solids by Weight	ASTM D 1644	73%
Solids by Volume	ASTM D 2697	68%
Weight Per Gallon	ASTM D 1147	8.4 lbs.
Tensile Strength	ASTM D 2370	700 psi
Elongation	ASTM D 2370	1000%
Movement	ASTM C 719	+/-25%
Skin Time	ASTM C 679	30 Minutes
Tack Free	ASTM C 679	3 Hours
Flash Point	ASTM D 56	103°F / 39°C
VOC	EPA 24	< 300 g/l

Above values are for White

Container Sizes: 10 oz. fiber cartridge

Colors: Clear, White, Black, Gray, Dark Gray, Clay, Sandstone, Wicker/Tan, Medium Bronze, Musket Brown, Royal Brown, Bronze, Aluminum

TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. **LIMITATION OF LIABILITY:** In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

**NOTE:** Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.