



#608 ALUMINUM ROOF COATING 2 Lb. – NON-FIBRATED

PRODUCT DESCRIPTION

#608 Aluminum Roof Coating is designed to provide a reflective surface for roofs, metal buildings, tanks, and mobile homes. Aluminum pigmented asphalt coatings can substantially reduce interior building temperature and prolong roof service life.

Lucas #608 Aluminum Roof Coating is formulated from specially refined asphalt, aromatic and aliphatic solvents, and 2 lbs. per gallon of ASTM D 962 leafing aluminum paste. Light brushing viscosity allows for quick and economical coverage.

APPLICATION

Surface to be coated must be dry and free of dirt or corrosion particles. It will be helpful to turn the pails upside down 24 hours prior to application so that the settled aluminum releases from the bottom of the pail. Before mixing, pour 50% of the liquid contents of the pail into a clean 5 gallon pail. All of the aluminum should remain in the original pail. Mix the aluminum into the liquid contents. When it is free of lumps, add back the liquid from the second pail, and mix until uniform. Mechanically mix coating thoroughly and continuously before and during application. Power mixing is recommended using a square bladed drywall mud mixer, and 1/2 inch drill is recommended for 5 gallon pails.

Apply evenly with a soft bristle brush or suitable spray equipment at the rate of not less than 0.75 gallon and not more than 1 gallon per 100 square feet. For best results, brush coating in one direction with the slope of the roof. Do not apply over fresh roof repairs or coating. Roofing asphalts, both hot and cold applied, contain oily constituents which may bleed through and stain the finished coating. As this condition is unpredictable, we recommend the user apply a small amount of #608 to the area of the roof to be coated, in order to test its performance. Use #608 as it comes from the container, no thinning is necessary with this product.

Clean Up: Tools and other equipment can be cleaned with mineral spirits. Take necessary precautions when handling combustible materials.

Storage: Keep from freezing. Keep out of direct sunlight. Do not heat or thin. Store between 40°F and 95°F. High temperatures and high humidity during storage will shorten the product's shelf life.

Shelf Life: One year from the date of manufacture.

*Roof surfaces must be dry for coating application. Even when the surface appears dry, moisture may be trapped in the roof, deck or insulation. A moisture scan is recommended prior to application. Application of this coating within 5°F of the dew point is not recommended.

WARNING! COMBUSTIBLE LIQUID AND VAPOR. Contains petroleum distillates. Keep away from heat and open flames. Avoid prolonged contact with or inhalation of solvent fumes. A NIOSH approved respirator with organic vapor cartridges is recommended. Do not take internally. If swallowed, do NOT induce vomiting. Contact medical personnel immediately. Read SDS prior to use. For professional use only. EMERGENCY CONTACT: CHEMTREC 1-800-424-9300.

#608 SPECIFICATION

ASTM D 2824 Type I

Viscosity	ASTM D 2196	150 cps
Solids by Weight	ASTM D 1644	50%
Solids by Volume	ASTM D 2697	50%
Weight Per Gallon	ASTM D 1147	7.9 lbs.
Reflectivity – Initial	ASTM C 1549	.64
Reflectivity – Aged	ASTM D 1549	.50
Emissivity	ASTM C 1371	.44
SRI	LEED	63
Flash Point	ASTM D 56	103°F / 39°C
VOC	EPA 24	< 450 g/l

Container Sizes: 1, 5, 55 gallon

Colors: Aluminum

This product is Florida Building Code approved.



To the extent allowed by local law, except as set forth below, seller makes no warranty of merchantability or fitness for any particular purpose with respect to the goods herein sold. There are no other warranties of any kind, expressed or implied, beyond the terms set forth on the face hereof. No employee or agent of the seller is authorized to alter the terms hereof.

Seller warrants that this product shall be free of any defect under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application.

LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, buyer's sole remedy shall be refunded of the purchase price or replacement of the defective material, at seller's option. Under no circumstances shall seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply, or may be invalid under the laws applicable to buyer's purchase or claim. In the event of any defect or failure of this product, consult local law to determine the applicability of any of the foregoing.

09/22/2025