



#9600 ALL PURPOSE URETHANE SEALANT

PRODUCT DESCRIPTION

Lucas #9600 All Purpose Urethane Sealant is a 100% solids non-shrinking moisture cure urethane sealant. It is intended for use in sealing joints, roof termination bars, and general repairs. Lucas #9600 has minimal odor and contains no solvents. It has excellent adhesion to concrete, masonry, EPDM, PVC, wood, vinyl, metal, Kynar®, and most other common building materials. Lucas #8015 TPO Primer is required for application on TPO roofs.

APPLICATION

To use this product, cut the tip to the desired size, a minimum of 3/8" is recommended, and then puncture the foil seal. The surface to be sealed must be clean and dry. The maximum recommended joint width is 2 inches. The maximum recommended depth is 1 inch. Use backer rod for deep joints. Additionally, it can be used to fill honeycombs, seal joints, and penetrations in below grade concrete or masonry walls. Lucas #9600 may be used with Lucas PolyPan® enclosures for through wall flashings and steep slope roofing applications. One cartridge can seal approximately 24 ft with a 1/4 inch bead.

Lucas #9600 is paint-able after 24 hours. Application below 32°F (0° C) is possible, however, curing requires free moisture in the air. The material will not begin to cure until the temperature is above freezing.

Clean up: Tools and other equipment can be cleaned with mineral spirits. Take necessary precautions when handling combustible materials.

Storage: Keep from freezing. Keep out of direct sunlight. Do not heat or thin. Store between 40°F and 95°F. High temperatures and high humidity during storage will shorten the product's shelf life.

Shelf Life: Two years from the date of manufacture.

CAUTION: Do not take internally. If swallowed, do **NOT** induce vomiting. Keep out of reach of children. Read SDS prior to use. EMERGENCY CONTACT: CHEMTREC 1-800-424-9300.

#9600 SPECIFICATION

ASTM C 920, Type S, Grade NS, Class 35, Use T, NT, M, G, A & O

Fed Spec TT-S-00230c, Class A, Type II

Canadian Standards Board CAN 19, 13-M87

Viscosity	ASTM D 2196	200,000 cps
Slump	ASTM C 693	No Sag
Solids by Weight	ASTM D 1644	100%
Solids by Volume	ASTM D 2697	100%
Hardness – Shore A	ASTM C 661	32
Tensile Strength	ASTM D 412	400 psi
Elongation	ASTM D 412	400%
Movement	ASTM C 719	+/-35%
Tack Free	ASTM C 679	2 Hours
Flash Point	ASTM D 56	None
VOC	EPA 24	8 g/l / < 1.5%

Container Size: 10 oz. / 296 ml plastic cartridge

Colors: White, Black, Bronze, Medium Bronze, Gray, Tan, Terra Cotta

To the extent allowed by local law, except as set forth below, seller makes no warranty of merchantability or fitness for any particular purpose with respect to the goods herein sold. There are no other warranties of any kind, expressed or implied, beyond the terms set forth on the face hereof. No employee or agent of the seller is authorized to alter the terms hereof.

Seller warrants that this product shall be free of any defect under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application.

LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, buyer's sole remedy shall be refunded of the purchase price or replacement of the defective material, at seller's option. Under no circumstances shall seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.